



DMV 304 HCu

1. Application

DMV 304 HCu has been designed for application as superheater and reheater boiler tube grade. 304 HCu has proved to be suitable in most advanced coal and lignite fired power stations for steam temperatures of up to approximately 600°C (1112°F) in supercritical and ultra supercritical vessel designs.

Carbon C 0.07-0.13	Chromium Cr 18	Nickel Ni 9	
Copper Cu 3	Niobium Nb (Cb) 0.45	Nitrogen N 0.05-0.12	Aluminium Al 0.003-0.03
Manganese Mn <1.00	Silicon Si <0.30	Phosphorus P <0.040	Sulfur S <0.010

Chemical composition nominal %

2. Main Features

- Austenitic stainless steel alloyed with Copper and Boron to increase the creep strength
- Very good high temperature corrosion resistance
- Very good creep resistance at high temperatures, specially in the range of 580°C (1076°F) to 640°C (1184°F)
- Inner surface shot peening treatment possible upon request

3. Description

3.1 Specifications

- 1.4907, X10CrNiCu Nb 18 9 3, European Steel registration
- UNS S 30432, 18Cr-9Ni-3Cu-Nb-N according to ASME SA-213/SA 213M, US Standard
- Cases of ASME Boiler and Pressure vessel Code Case 2328-1, March 6, 2003, United States
- Following VdTÜV Material Data Sheet 550, Federal Republic of Germany

3.2 Available Sizes

DMV 304 HCu is produced as seamless austenitic tube, suitable for all recently used austenitic reheater and superheater boiler tube sizes. Following VdTÜV Material Data Sheet 550, the max. outer diameter is 65 mm and the max. wall thickness is 12.5 mm. Other sizes are available upon request.

3.3 Chemical composition

Mass % according ASME Case 2328-1, March 6, 2003.

	%min	%max
C	0.07	0.13
Si		0.30
Mn		1.00
P		0.040
S		0.010
Cr	17.00	19.00
Ni	7.50	10.50
Nb (Cb)	0.30	0.60
Cu	2.50	3.50
N	0.05	0.12
Al	0.003	0.030
B	0.001	0.010

3.4 Mechanical Properties

3.4.1 At Solution Annealed Condition

According ASME Code Case 2328-1.

	MPa	ksi
Y.S. min.	(235)	34
U.T.S. min.	(590)	85
E in 2" min., %		35

1 MPa=1 N/mm²; 1 ksi=6.9 MPa
() = calculated values

Following VdTÜV Material Data Sheet 550.

	MPa	ksi
0.2% Y.S. min.	235	(34.1)
1.0% Y.S. min.	270	(39.2)
U.T.S.	590-850	(85.6-123.3)
A %		35

() = calculated values

3.4.2 Impact Resistance

According VdTÜV Material Data Sheet 550, the impact resistance KV in longitudinal direction is min 85J. (Average value from 3 specimens. The average value may fall short only with one specimen, and only by max. 30%).

3.4.3 At Elevated Temperature

Following VdTÜV Material Data Sheet 550.

Temp °C	(°F)	0.2% Y.S. min MPa (ksi)	1.0% Y.S. min MPa (ksi)
100	(212)	205 (29.7)	230 (33.4)
200	(392)	180 (26.1)	205 (29.7)
300	(572)	170 (24.7)	195 (28.2)
400	(752)	160 (23.2)	185 (26.8)
450	(842)	175 (25.4)	195 (28.2)
500	(932)	150 (21.8)	175 (25.4)
550	(1022)	145 (21.0)	170 (24.7)
600	(1112)	140 (20.3)	165 (23.9)
650	(1202)	135 (19.6)	160 (23.2)
700	(1292)	135 (19.6)	160 (23.2)
750	(1382)	125 (18.1)	150 (21.8)

() = calculated values

3.4.4 Creep Strength Values

Average Preliminary creep strength values for 10,000 h and 100,000 h acc. to VdTÜV Material Data Sheet 550. The lower scale band can be estimated as 20% lower than average values.

Temp	10,000h	100,000h
°C	MPa (ksi)	MPa (ksi)
600	240 (34.8)	182 (26.4)
610	222 (32.2)	165 (23.9)
620	206 (29.9)	152 (22.0)
630	192 (28.4)	139 (20.2)
640	174 (25.2)	126 (18.3)
650	160 (23.2)	116 (16.8)
660	146 (21.2)	105 (15.2)
670	134 (19.4)	96 (13.9)
680	124 (18.0)	86 (12.5)
690	114 (16.5)	78 (11.3)
700	101 (14.6)	68 (9.9)
710	92 (13.3)	61 (8.8)
720	84 (12.2)	54 (7.8)
730	76 (11.0)	48 (7.0)
740	68 (9.9)	42 (6.1)
750	61 (8.8)	37 (5.4)

() = calculated values

3.5 Physical Properties

Coefficient of Thermal Expansion following VdTÜV Material Data Sheet 550.

Coefficient of Thermal Expansion between 20°C (68°F) and...			
Temperature	10 ⁻⁶ /K	10 ⁻⁶ /F	
°C	(°F)		
100	16.4	(9.11)	
200	17.1	(9.5)	
300	17.5	(9.72)	
400	17.8	(9.89)	
500	18.1	(10.1)	
600	18.4	(10.2)	
700	18.6	(10.3)	
750	18.7	(10.4)	

() = calculated values

Thermal Conductivity following VdTÜV Material Data Sheet 550.

Thermal Conductivity			
Temperature	W/(m°C)	Btu /	
°C	(°F)	(ft h °F)	
20	14.5	(8.38)	
100	16.2	(9.36)	
200	19.4	(11.2)	
300	21.5	(12.4)	
400	23.0	(13.3)	
500	25.2	(14.6)	
600	28.6	(16.5)	
700	31.0	(17.9)	
750	31.0	(17.9)	

() = calculated values

Modulus of Elasticity following VdTÜV Material Data Sheet 550.

Modulus of Elasticity			
Temperature	10 ³ MPa	10 ³ ksi	
°C	(°F)		
20	189	(27.4)	
100	182	(26.4)	
200	174	(25.2)	
300	165	(23.9)	
400	156	(22.6)	
500	149	(21.6)	
600	141	(20.5)	
700	134	(19.4)	
750	130	(18.9)	

() = calculated values

4 Application Properties

4.1 Heat Treatment

The heat treatment of cold finished DMV 304 HCu meets the requirement of VdTÜV Material Data Sheet 550, where an annealing temperature of the tubes between 1100°C (2012°F) and 1180°C (2156°F) is required. Additionally, the requirements of ASME Code Case 2328-1 are met where solution-treatment at 2000°F (1093°C) minimum is specified.

4.2 Corrosion Properties

The DMV 304 HCu is designed for the application in furnace atmospheres at high temperature in the range of 580°C (1076°F) to 640°C (1184°F) and has a good corrosion resistance in such atmospheres.

4.3 Tube Bending

DMV 304 HCu is generally suitable for further cold or hot forming.

After hot forming a new solution annealing is necessary, in case the hot forming has not followed a controlled temperature process between 1100°C (2012°F) and 1150°C (2102°F).

Following the VdTÜV Material Data Sheet 550, cold formed tubes have to be newly solution annealed if the forming degree is > 25% or the R/D ratio is < or equal 2.0. For corrosion reasons, it is recommended to perform a new solution annealing even following smaller forming degrees.

4.4 Welding

Pre-heating and a heat treatment after welding are not necessary. To avoid hot cracks in the weld metal, the processes recommended by the filler producers have to be observed.

Only approved filler materials should be considered, that have been tested for the foreseen application temperature. The calculation values for the filler materials should be considered.

Details on our extensive customer and project references available upon request.

While our Company has compiled and organized this data to the best of its knowledge, the data is provided on an "as is" basis only. To the fullest extent permissible by applicable law, we neither make any representation nor give any warranty -neither express, implied or statutory- regarding this data, including, but not limited to, with respect to completeness, accuracy, reliability, security, timeliness, fitness or suitability for any particular purpose, merchantability or any decisions you may make based on it. To the same extent, our company does not assume any other liability regarding this data for any direct, indirect or consequential or any other losses or damages of whatsoever kind (whether based on contract, tort, delict, warranty or any other legal theory) resulting from its use. The use of this data is at your own risk, unless otherwise agreed in writing. Our company reserves the right to modify its content at its own discretion at any time and without prior notice."