



# DMV 800 H

## 1. Applications

DMV 800 H is the material of choice for a wide range of applications like:

- Heating element sheathing because of good mechanical strength
- Ethylene pyrolysis tubing due to resistance to carburization and good mechanical properties
- Steam super-heater tubing owing to good mechanical strength and resistance to steam
- Furnace components

Carbon <b>C</b> 0.05-0.10	Nickel <b>Ni</b> 32	Chromium <b>Cr</b> 20.5	
Aluminium <b>Al</b> 0.20-0.6	Titanium <b>Ti</b> 0.20-0.60	Copper <b>Cu</b> <0.50	
Manganese <b>Mn</b> <1.5	Silicon <b>Si</b> 0.20-0.60	Phosphorus <b>P</b> <0.015	Sulfur <b>S</b> <0.015

Chemical composition nominal %

## 2. Main Features

DMV 800 H is an austenitic solid-solution grade containing small amounts of precipitated titanium nitrides and carbides, carbon nitrides and chromium carbides. During long term exposure below 700°C (1292°F) γ'-phase may be formed, lowering the ductility. Therefore, please check carefully the standards regulation and chemical composition for the intended application.

## 3. Description

### 3.1 Specifications

- UNS N08800 a. UNS N08810 acc. to ASTM A 213 and ASME SA 213
- UNS N08800 a. UNS N08810 acc. to ASTM A 312 and ASME SA 312
- 1.4558, 1.4958 and 1.4959 acc. to EN 10216-5

\* Please check the responding chemical analysis modification with our technical department.  
[ UNS N08811 is available on special request. ]

### 3.2 Chemical composition

DMV 800 H contains:

	%min	%max
<b>C</b>	0.05	0.10
<b>Si</b>	0.20	0.60
<b>Mn</b>		1.50
<b>P</b>		0.015
<b>S</b>		0.015
<b>Cr</b>	19.00	22.00
<b>Ni</b>	30.00	34.00
<b>Al</b>	0.20	0.60
<b>Ti</b>	0.20	0.60
<b>Cu</b>		0.50
<b>Fe</b>	39.5	

## 3.3 Mechanical Properties

### 3.3.1 Tensile Properties at 20°C (68°F) Annealed Condition

UNS N08800\* acc. to ASTM B 407:  
Cold worked annealed:

	MPa	ksi
<b>0.2% Y.S. min.</b>	205	30
<b>U.T.S. min.</b>	520	75
<b>E in 2" min., %</b>		30

UNS N08800\* acc. to ASTM B 407 and UNS N08810\* acc. to ASTM B 407: Hot-finished annealed:

	MPa	ksi
<b>0.2% Y.S. min.</b>	170	25
<b>U.T.S. min.</b>	450	65
<b>E in 2" min.</b>		30

Grade 1.4958 / 1.4959 according to EN 10216-5:

	MPa	ksi
<b>0.2% Y.S. min.</b>	170	(25)
<b>1.0% Y.S. min.</b>	200	(29)
<b>U.T.S. min.</b>	500	(72)
<b>A</b>		30%

1 MPa=1 N/mm<sup>2</sup>; 1 ksi=6.9 MPa  
( ) = calculated values

### 3.3.2 Tensile Properties at Elevated Temperature

Grade 1.4958 and 1.4959 acc. to EN 10216-5:

Temp	0.2% Y.S. min		1.0% Y.S. min	
°C	(°F)	MPa (ksi)	MPa (ksi)	
100	(212)	140(20.3)	160(23.2)	
150	(302)	127(18.4)	147(21.3)	
200	(392)	115(16.7)	135(19.6)	
250	(752)	105(15.2)	125(18.1)	
300	(572)	95(13.8)	115(16.7)	
350	(662)	90(13.0)	110(15.9)	

Temp	0.2% Y.S. min		1.0% Y.S. min	
°C	(°F)	MPa (ksi)	MPa (ksi)	
400	(752)	85(12.3)	105(15.2)	
450	(842)	82(11.9)	102(14.8)	
500	(932)	80(11.6)	100(14.5)	
550	(1022)	75(10.9)	95(13.8)	

( ) = calculated values

### 3.3.3 Impact Test at 20C (68F)

Acc. to EN 10216-5 the notch impact energy at 20°C (68°F) must be minimal 100 J in longitudinal and 60 J in transversal direction (average value of three samples with min. 70 J/cm<sup>2</sup>, longitudinal and 40 J/cm<sup>2</sup> transversal individual value).

### 3.3.4 Creep Rupture Strength

For grade 1.4958 and 1.4959 the following creep rupture strength values for 10,000 h and 100,000 h are listed in EN 10216-5:

#### Grade 1.4958

Temp	10,000h		100,000h	
°C	(°F)	MPa (ksi)	MPa (ksi)	
500	(932)	290(42.0)	215(31.2)	
550	(1022)	225(32.6)	160(23.1)	
600	(1112)	140(20.3)	95(13.8)	
650	(1202)	97(14.1)	63(9.1)	
700	(1292)	69(10.0)	44(6.4)	

( ) = calculated values

#### Grade 1.4959

Temp	10,000h		100,000h	
°C	(°F)	MPa (ksi)	MPa (ksi)	
700	(1292)	290(42.0)	215(31.2)	
750	(1382)	225(32.6)	160(23.1)	
800	(1472)	140(20.3)	95(13.8)	
850	(1562)	97(14.1)	63(9.1)	
900	(1652)	69(10.0)	44(6.4)	
950	(1742)	69(10.0)	44(6.4)	
1000	(1832)	69(10.0)	44(6.4)	

( ) = calculated values

### 3.4 Physical Properties

Coefficient of Thermal Expansion between 20°C (68°F) and...			
Temperature °C	(°F)	10 <sup>-6</sup> /°K	10 <sup>-6</sup> /°F
100	(212)	14.4	(8.0)
200	(392)	15.2	(8.4)
400	(752)	16.2	(9.0)
600	(1112)	17.0	(9.4)
800	(1472)	17.2	(9.9)
1000	(1832)	18.8	(10.6)

( ) = calculated values

Thermal Conductivity			
Temperature °C	(°F)	W/(m°C)	Btu / (ft h °F)
20	(68)	11.6	(6.71)
100	(212)	13.0	(7.51)
200	(392)	15.0	(8.67)
400	(752)	17.8	(10.3)
600	(1112)	21.0	(12.1)
800	(1472)	24.5	(14.2)
1000	(1832)	29.0	(16.8)

( ) = calculated values

Modulus of Elasticity			
Temperature °C	(°F)	10 <sup>3</sup> MPa	10 <sup>3</sup> ksi
20	(68)	198	(28.7)
100	(212)	193	(28.0)
200	(392)	187	(27.1)
400	(752)	173	(25.1)
600	(1112)	158	(22.9)
800	(1472)	144	(20.9)
1000	(1832)	127	(18.4)

( ) = calculated values

### 3.5 Corrosion Properties

For applications reinforcing high temperature oxidation the high chromium and nickel contents of DMV 800 H make it eminently suitable for use in non sulphurous, oxidizing atmospheres up to 1000°C (1832°F) even under non isothermal conditions.

Since DMV 800 H contains iron, it has a high resistance to internal oxidation, which normally affects Nickel-Chromium alloys.

In other atmospheres, like carburization due to the high Nickel and Chromium content, DMV 800 H has a very good resistance:

While our Company has compiled and organized this data to the best of its knowledge, the data is provided on an "as is" basis only. To the fullest extent permissible by applicable law, we neither make any representation nor give any warranty -neither express, implied or statutory- regarding this data, including, but not limited to, with respect to completeness, accuracy, reliability, security, timeliness, fitness or suitability for any particular purpose, merchantability or any decisions you may make based on it. To the same extent, our company does not assume any other liability regarding this data for any direct, indirect or consequential or any other losses or damages of whatsoever kind (whether based on contract, tort, delict, warranty or any other legal theory) resulting from its use. The use of this data is at your own risk, unless otherwise agreed in writing. Our company reserves the right to modify its content at its own discretion at any time and without prior notice.\*

higher than that of 25% Cr-20% Ni steels. The protective oxide layer which is formed is adherent in both, static and cyclic conditions of heating and cooling. Resistance to carburization is enhanced as soon as a thin layer of oxide is formed on the surface.

Resistivity to hydrogen is excellent, so that DMV 800 H is the preferred material used in the production of hydrogen in steam / hydrocarbon reforming processes.

DMV 800 H also shows a good resistance in the presence of hydrogen sulphide up to about 400°C (752°F).

2192°F). DMV 800 H is susceptible to relaxation cracking if solution annealed materials are exposed to service temperatures within the range of 550°C - 750°C (1020°F - 1380°F).

During subsequent service a high degree of cold deformation and welding during fabrication enhances the susceptibility to relaxation cracking.

A stabilizing heat treatment at about 980°C (1800°F) for 3 hours has been shown to alleviate susceptibility to relaxation cracking. This has been proved for new material prior to fabrication and for material which has already been in service prior to repair welding.

As for all austenitic stainless steels, the cleanliness requirements (especially contamination from greases) must be strictly observed.

The furnace atmosphere must have very low sulphur content.

When subsequently used in a moist environment, oxidation must be avoided by use of highly reducing atmosphere (cracked ammonia, hydrogen, ...) or removed by pickling after heat treatment.

### 5.2 Bending

DMV 800 H is generally suitable for further cold or hot forming.

Cold bending of tubes can be carried out under similar conditions to those required for austenitic stainless steels.

Cold formed tubes and pipes have to be newly solution annealed if the forming degree is > 20% or the R/D ratio < or equal 2.5.

For corrosion reasons, it is sometimes recommended to perform a new solution annealing even following smaller forming degrees.

### 5.3 Welding

Preheating and heat treatment after welding are not necessary.

To avoid hot cracks in the weld metal, processes recommended by the filler producers have to be observed. Only approved filler materials should be considered, that have been tested for the foreseen application temperature. The calculation values for the filler materials should be respected.

To eliminate the risk of relaxation cracking, material exposed to service temperature above 550°C (1022°F) should obey strictly the mentioned instructions in chapter "5.1 Heat Treatment" of this datasheet.

## 4. Supply

### 4.1 Dimensional Range

NOMINAL DIMENSIONAL RANGE		
Cold Finished		
Outside Diameter	mm	inch
min	1.6	0.063
max	244.5	9.626
Wall thickness	mm	inch
min	0.1	0.004
max	40	1.575

Hot Finished		
Outside Diameter	mm	inch
min	32	1.260
max	280	11.024
Wall thickness	mm	inch
min	2.8	0.110
max	60	2.362

### 4.2 Delivery Condition

Tubes and pipes are delivered in cold or hot finished condition depending on size and specification. Normally they will be supplied in annealed condition.

### 4.3 Long lengths, 'U' bent

Our tubes are also available in U-bent version in lengths of up to 30 m (straight); the high deformability of the material allows cold bending down to a very small bending radius.

## 5. Fabrication

### 5.1 Heat Treatment

To ensure complete recrystallization and a homogeneous chromium distribution, solution annealing should be carried out in a temperature range of 1150°C - 1200°C (2102°F -